

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



AI

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)


(51) International Patent Classification ⁵ : C08L 23/02	A1	(11) International Publication Number: WO 94/22948 (43) International Publication Date: 13 October 1994 (13.10.94)
<p>(21) International Application Number: PCT/FI94/00110</p> <p>(22) International Filing Date: 25 March 1994 (25.03.94)</p> <p>(30) Priority Data: 931343 26 March 1993 (26.03.93) FI</p> <p>(71) Applicant: BOREALIS POLYMERS OY [FI/FI]; P.O. Box 330, FIN-06101 Porvoo (FI).</p> <p>(72) Inventors: HARLIN, Ali; Kärppärinne 1, FIN-01450 Vantaa (FI). PALMQVIST, Ulf; Hansatie 2, FIN-06150 Porvoo (FI).</p> <p>(74) Agent: NESTE OY; Patent Services, P.O. Box 310, FIN-06101 Porvoo (FI).</p>		<p>(81) Designated States: CA, CN, NO, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>With international search report.</i></p>

(54) Title: **PROCESS FOR MANUFACTURING OLEFIN POLYMERS AND PRODUCTS PREPARED BY THE PROCESS**

(57) Abstract

A process for manufacturing bimodal olefin polymers and copolymers having a ratio between low molecular weight fractions and high molecular weight fractions within the range of 40:60-70:30, by mixing under shear conditions 5-50 per cent by weight of a low molecular weight unimodal polyolefin having a molecular weight (M_w) between 15,000-30,000, and 95-50 per cent by weight

of a bimodal polyolefin having a ratio between low molecular weight fractions and high molecular weight fractions within the range of 30:70-55:45. According to the preferred embodiment there is used a multi-phase process comprising a loop reactor followed by a gas-phase reactor, wherein a part of the product coming out from the loop reactor is separated and combined with the bimodal product coming out from the gas-phase reactor.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

Process for manufacturing olefin polymers and products prepared by the process

Field of the invention

5

The invention concerns a process for manufacturing olefin homo- and copolymers having a bimodal molecular weight distribution. Especially the invention concerns a process for manufacturing bimodal olefin polymers for film, pipe or blow molding products and products prepared by the process.

10

Background of the invention

Recently high density polyethylene has achieved commercial success in such products as films, pipes and blow moulding materials. Among these new polymers are high molecular weight high density polyethylene resins having a broad molecular weight distribution.

15

Polyethylene resins manufactured by using modern high productivity catalysts have often relatively narrow molecular weight distribution. These resins are not ideal for the manufacture of high density polyethylene for extrusion, eg. film, pipe or molding resins.

20

Bimodal polyethylenes are polymers, which are composed of low and high molecular weight fractions. These polymers are designed to have a certain balance between fair processability and good mechanical strength properties. The low molecular weight fractions improve the processability properties of the polymer and the high molecular weight fractions improve mechanical properties. In order to increase strength properties the proportion of high molecular weight fractions could be increased. The result is, however, that the product becomes more difficult to process, for example in film extruders. The processing consumes more energy and the surface quality of the films or pipes tend to be inferior. In other words the processability of the product sets certain limits to the proportion of the high molecular weight component. On the other hand the processability can be improved by using as the first component a polymer having very low molecular weight.

25

30

In practise it has been found that in view of product properties the low molecular weight

- component has preferably the following properties: a weight average molecular weight (M_w) of 5,000-25,000, a ratio between the weight average molecular weight and the number average molecular weight (M_n) of 2.5-9 and a density of 0.960-0.980 g/cm³ for bimodal high density polymer and 0.925-0.940 g/cm³ for bimodal low density polymer.
- 5 The melt index (MFR_2) of this fraction is typically within the range of 10-1000 g/10 min. The molecular weight of the bimodal end product is between 150,000-400,000, typically 200,000-350,000 and the ratio M_w/M_n is between 20-40. By calculating from these values or experimentally it is obtained for the high molecular weight component typical M_w -values of about 400,000-900,000, M_w/M_n -values of 4.5-9.5 and densities for bimodal high
- 10 density materials of 0.930-0.960 g/cm³ and for bimodal low density materials 0.900-0.920 g/cm³. The proportions between the low molecular weight component and the high molecular weight component vary typically between 40:60 - 65:35 for bimodal polyethylene resins.
- 15 According to prior art polyethylene resins having a broad molecular weight distribution are manufactured by two principal methods. The first method consists of blending two or more unimodal polymers having a different molecular weight. The first component can have a greater proportion of relatively low molecular weight fractions and the further components can have a greater proportion of high molecular fractions. Such method is
- 20 disclosed for example in European patent n:o 0 100 843, in which polyethylene is manufactured by blending together 60-30 parts by weight of a low molecular weight high density ethylene polymer having a melt index (MI) within the range of 45-300 g/10 minutes and a density of 0.950-0.975 g/cm³, and 40-70 parts by weight of a high molecular weight high density ethylene polymer having a melt index (MFR_{21}) within the
- 25 range of 0.1 - 1.5 g/10 min and a density within the range of 0.930-0.945 g/cm³. Another example of blending two unimodal polyethylene components together is EP533160. Also it is known to blend two or more unimodal polyethylene components having different ranges of molecular weights (see EP129312) or blend an unimodal polyethylene component and a bimodal polyethylene component (see EP517222).
- 30
- The second basic method for producing ethylene polymers having a broad molecular weight distribution consists of a multiphase polymerization process, in which in one reactor a polymer having a low molecular weight and a narrow molecular weight

distribution is prepared. Another polymerization reactor is run under conditions, which favor the formation of polymers having a high molecular weight. The reactors are in series so that the polymerization started in the first reactor continues in the second one. In this way it is possible to obtain bimodal ethylene polymers. Also it is known to blend
5 unimodal polyethylene components and bimodal components prepared by a multi-phase process (see EP129312).

Both methods above have certain drawbacks. In the blending method it has been found that the gel content and the number of the fish-eyes in the blended product tend to be high.
10 Another drawback in the method is that the possibilities to grade changes are very limited. The only possibility to affect the product properties is to vary the proportions of the blend components, which can be made only within certain limits. Very often a grade change requires selection of components having different molecular weights and/or different densities. This means that the producer has to keep several different blending components
15 available, which demands great investments to storage facilities.

In the continuous multiphase polymerization method the process control is more complicated than in the single-phase polymerization. The transition times are long, especially when the conditions in the first reactor must be adjusted.

20

In the continuous multiphase polymerization method there are also some drawbacks in the product homogeneity. Batch-polymerized bimodal resins can be gel-free, because all particles have the same residence time and composition. A continuous process to produce a bimodal resin in back-mixed reactors gives a mixture of particles with a composition
25 ranging from pure low molecular weight materials to pure high molecular weight materials.

Because of the residence time distribution a part of the material flows immediately through the first reactor forming in the second reactor a lot of high molecular weight
30 fraction. The composition distribution between the particles can be affected either by narrowing the residence time distribution in the first reactor, or removing the small unreacted or less reacted catalyst particles from the polymer before it is fed to the second reactor.

Resins with good mechanical properties can be achieved when in the first reactor a higher proportion of low molecular weight material and in the second reactor a material of very high molecular weight is produced. However the homogeneity of the end product will decrease drastically because of composition distribution between particles. Products having
5 a reactor split higher than 55:45 have generally high gel and fish-eye content in the end product.

The expression "reactor split" used in this application means the ratio of the low molecular weight material to the high molecular weight material in a reactor product. The
10 expression "product split" means the corresponding ratio in the end product.

Without limiting to any specific theory one possible explanation is that if more low molecular weight material (by volume) is produced than high molecular weight material, the shear forces during melt homogenization will not be conveyed easily to the areas of
15 high molecular weight. The high molecular weight particles just tend to float around in the low molecular weight/low viscosity fraction and show up as gels or white spots in the end product.

The inhomogenities can be avoided if lower reactor splits, for example 45:55 is used.
20 However, this is not favorable for combination of good processability and good mechanical performance. To achieve bimodal polymers having reasonably good processing properties, eg. for film or pipe grade polymers, it is necessary to increase the reactor split, which leads to the drawbacks mentioned above.

25 Summary of the invention

According to the invention it has been surprisingly found that it is possible to homogeneously mix a certain amount of low molecular weight unimodal material to a bimodal material produced in a multiphase polymerization and having a relatively low reactor split,
30 thereby obtaining an end product with a relatively high product split without excessive formation of gel-like agglomerates.

Therefore one object of the invention is a process for manufacturing bimodal olefin

homopolymers and copolymers, in which the proportion of the low molecular weight component to the high molecular weight component in the end product (product split) is relatively high without causing excess formation of gels and fish-eyes and which materials have good processability and good mechanical properties.

5

This object is achieved in the process according to the invention for producing bimodal olefin homopolymers or copolymers, said process comprising melting and mixing together under shear forces at least two polymer components of

- 10 (a) 5-50 percent by weight of an unimodal low molecular weight olefin polymer having a weight average molecular weight (M_w) within the range of 15,000 to 30,000 and a ratio between the weight average molecular weight (M_w) and the number average molecular weight (M_n) within the range of 2.5-9 and a melt index of 10-1000 g/10 min ($MFR_2, 190^\circ\text{C}$); and

15

- (b) 95-50 percent by weight of a bimodal olefin polymer containing 30-55 per cent by weight of low molecular weight polyolefin fractions having properties as defined for component (a) above and 70-45 per cent by weight of polyolefin fractions having a molecular weight sufficiently high to achieve in the end product formed by components (a) and (b)
- 20 a weight average molecular weight (M_w) within the range 150,000-400,000, M_w/M_n between 10-40 and a ratio between low molecular weight fractions and high molecular weight fractions (product split) of 40:60-70:30.

Detailed description of the invention

25

- As mentioned above the invention is based on a discovery that a certain amount of low molecular weight olefin polymer can be melt-mixed with a bimodal olefin polymer having a reactor split between of 30:70 - 55:45 without formation of excessive amounts of gels. With a definition "olefin polymers" throughout the specification it is meant homopolymers and copolymers of olefin monomers such as ethylene, propylene, butene, hexene, 4-
- 30 methyl-1-pentene and the like. A preferred olefin is however ethylene and the invention will be hereinafter described as applied to manufacturing bimodal ethylene polymers, although same kind of problems may be also found in polymerization of other olefin

monomers and the same problems can be solved according to the invention.

The low molecular weight component can be an ethylene polymer having a weight average molecular weight (M_w) in the range of 15,000-30,000 and a ratio of the weight average molecular weight and the number average molecular weight (M_n) within the range of 2.5-9 and a melt index (MFR_2) preferably between 10-1000 g/10 min. The density of the polymer can vary between 0.930-0.980 g/cm³. This polymer component can be produced by any polymerization method giving the above-mentioned properties. Thus this process can be a slurry or a gas-phase polymerization process.

10

The second component for producing bimodal ethylene polymers according to the invention is a bimodal ethylene polymer containing low molecular weight fractions having a weight average molecular weight (M_w) within the range of 15,000 to 30,000 and a ratio of the weight average molecular weight and the number average molecular weight (M_n) within the range of 2.5-9 and high molecular weight fractions having a calculated M_w within the range of 250,000-700,000 and M_w/M_n with the range of 4.5-9.5. The ratio of the low molecular weight material to the high molecular weight material in the bimodal product (reactor split) is selected so that it is within the range of 30:70-55:45.

Also the bimodal component can be produced by any method producing a product having properties mentioned above. Therefore this product can be produced by slurry-slurry polymerization, slurry-gas phase polymerization or gas phase-gas phase polymerization obtaining bimodal polymer having the properties above and melt indexes of 0.05-10 (MFR_5) or 0.5-50 (MFR_{21}) and density of 0.915-0.960 g/cm³. A slurry-gas phase process is especially preferred.

Thus according to the invention it is possible to achieve the desired results by melt-mixing said unimodal low molecular weight component and said bimodal component in such proportions that the ratio of low molecular weight material to high molecular weight material (product split) is within the range of 40:60-70:30. In practise this ratio can be achieved when 5-50, preferably 10-50 percent by weight of low molecular weight material is melt-mixed with 95-50, preferably 90-50 percent by weight of bimodal material to produce an end product polymer having M_w preferably within the range of 150,000-

30

400,000 and M_w/M_n between 10-40, high load melt index between 1-60 (MFR₂₁) and density between 0.940-0.960 g/cm³.

5 The two main components for obtaining the ethylene polymers of the invention can be originated from different sources or they can be originated from the same multiphase process. Therefore according to one embodiment of the invention any low molecular weight unimodal polymer and any bimodal polymer having the properties defined above can be melt-mixed to a bimodal ethylene polymer having a product split between the low molecular weight material and the high molecular weight material as specified above.

10

However according to a preferred process embodiment of the invention bimodal ethylene homopolymers and copolymers are produced in at least one polymerization step sequence comprising polymerizing in a first polymerization step low molecular weight olefin polymer having a weight average molecular weight (M_w) within the range of 15,000 to 15 30,000 and a ratio between the weight average molecular weight (M_w) and the number average molecular weight (M_n) within the range of 2.5-9, introducing said polymer into a second polymerization step for producing olefin polymer containing said low molecular weight polymer and high molecular weight olefin polymer having a calculated M_w within the range of 250,000-700,000 and a ratio of M_w/M_n within the range of 4.5 to 9.5, the 20 product formed in the second polymerization step having a ratio between the low molecular weight material and the high molecular material within the range of 30:70-55:45. According to the invention 5-50 per cent by weight of the polymer formed in said first polymerization step is separated and melt-mixed with the product of the second polymerization step. This separated polymer portion is therefore not introduced to the second 25 polymerization step. Instead it is combined and melt-mixed with the product coming out from the second polymerization step to form a polymer composition having a ratio of low molecular weight polymer fractions to high molecular weight fractions (product split) within the range of 40:60-60:40, preferably 45:55-60:40.

30 The mixing can be carried out by introducing the portion separated from the first polymerization step into the melt extruder, for example the pelletizing extruder, in which the second polymerization step product is melted and pelletized. In other words the first polymerization step product is blended with the second polymerization step product. It is

also possible to melt the portion separated from the product of the first polymerization step separately and introduce this melt to the melting device for the product of the second polymerization step by using for example a side feed extruder attached to the pelletizing or homogenizing extruder.

5

Several advantages can be achieved in this way. First, in the second polymerization step a bimodal product can be formed, in which the ratio of the low molecular weight material to the high molecular weight material is within a favorable range in view of the homogeneity of the product, eg. between 30:70-50:50, but in the end product said ratio is
10 between 50:50-70:30, whereby the product has good mechanical properties and processability without excessive formation of gels. Secondly, the process according to the invention makes it possible to affect the molecular weight of the end product and the total reactor split without necessarily changing the polymerization conditions in the second polymerization step. The grade changes of the end product become more easy and the
15 total control of the process becomes quicker and more easy.

The separation of a portion from the first polymerization step is known as such. For example Japanese patent applications JP89221002 and JP89221003 disclose a process for manufacturing propylene-ethylene block copolymers, whereby in a first polymerization
20 step liquid propylene is polymerized at slurry phase and said polypropylene slurry is fed into a gas-phase polymerization step, in which propylene-ethylene copolymer is polymerized. According to these publications the slurry from the first polymerization step is divided to a slurry containing mainly fine particles and to a slurry containing mainly coarse particles. The fine particles are returned to the slurry polymerization and the coarse
25 particles are introduced into the gas-phase polymerization. With this method the advantages of this invention cannot be achieved.

According to the invention the separation of a part of the first reactor product can be carried out by any suitable method and device. In the case that both reactors are slurry
30 polymerizations, for example loop-loop polymerization process, the separation is easy because the slurry flow can be simply divided into two streams. In the case that the first reactor is a slurry polymerization reactor and the second reactor is a gas-phase reactor, the product from the first reactor can be divided into two streams either before or after

separation of the diluent. In the case that both reactors are gas-phase reactors, the product stream can be divided into two streams after the monomers are separated by flashing.

One preferable alternative is to use the classification of the product flow from the first reactor. This can be carried out by using known classifiers such as liquid cyclone classifier/concentrators or a combination of a concentrator and hydraulic sedimentation classifiers. If in the classification the fine particles from the first reactor product flow can be separated at least partly and introduced after by-passing the second gas-phase reactor to the end product, an additional advantage is achieved. The fine particles coming from the first reactor contain very little low molecular weight material and since they tend to be very active in the second reactor, the fraction of high molecular weight material in these particles becomes very high. Due to this they become very difficult to homogenize in the compounding step. The fact that the fines are catalytically very active means that they tend to cause local overheating and formation of agglomerates, which leads to increased amount of gels in the end product.

In the process according to the invention any suitable catalysts, which give the desired molecular weight properties to the polymer products, can be used. Preferable catalysts are Ziegler-type catalysts, although other catalyst types such as chromium catalysts or metallocene-catalysts can be used, when possible. These catalysts can be used with any known cocatalysts in either one or both reactors. It is also possible to use catalysts only in the first polymerization step or in both steps or different type of catalysts can be used in producing low molecular weight polymers and bimodal polymers containing both low molecular weight material and high molecular weight material.

Preferable catalysts are for example those disclosed in Finnish patent applications FI916192, FI905523, FI904523, FI902123, FI901895, FI900842, FI906323, FI895703, FI895526, FI894216, FI893621, FI892153 and FI862459. However it is to be noted that the process according to the invention is not a catalyst specific process and therefore any catalyst giving an appropriate activity and a controllable molecular weight can be used in the process according to the invention.

The invention is further illustrated by referring to the accompanying figures, in which

Figure 1 shows as a diagram the general principle of the method according to the invention;

Figure 2 shows as a diagram one embodiment of the process according to the invention,
5 in which a part of the first step product is passed-by the second step polymerization and dry-blended with the product of the second step polymerization; and

Figure 3 discloses a modification of the process of Figure 2, in which a part of the first step polymerization product is melted in a side-feed extruder attached to the pelletizing
10 extruder for the second step polymerization product.

In Figure 1 there is disclosed the general principle of the process according to the invention. The first step polymerization is carried out in the first reactor 10 by feeding the reactants via line 11. The reactants are polymerizable monomers, comonomers, hydrogen,
15 diluents, catalysts etc. The reactor 10 can be of any type, such as a slurry reactor, for example a stirred-type reactor, loop reactor etc. The low molecular weight polymer from reactor 10 is taken away through line 12 and transferred to the second reactor 20. Monomers, comonomers, hydrogen, catalyst and cocatalyst components etc. can be fed to the reactor 20 through feed systems referenced by line 21. The product of the second
20 reactor containing low molecular weight fractions and high molecular weight fractions is taken from reactor 20 through line 22 and transferred to a pelletizing or homogenizing mixer or extruder 30. The end product is taken from extruder 30 through line 31. The second step reactor 20 can likewise be of any type such as a slurry reactor or gas-phase reactor.

25

According to the invention a part of the product of the first step reactor 10 is separated from the product transfer system represented by line 12 and is passed-by the second reactor 20 through line 13 and combined with the product coming from the second step reactor 20 through line 22.

30

In Figure 2 the product coming out from the first reactor 10 through line 12 is transferred to a separation unit 13, which serves to separate unreacted monomers and diluents from the polymer product in the case that the reactor 10 is for example a slurry polymerization

reactor. The separated gaseous and other components are returned to the reactor 10 through line 14. The separation unit 13 can function also as a device for separating from the polymer product a portion of the polymer, which is transferred through line 16 into an optional additional separation unit 17. It can be used to separate unreacted components
5 such as monomers, hydrogen or diluents from the polymer. These components can be removed through line 18.

Corresponding separation units can be used in connection of the second reactor 20. Thus the polymer from the reactor 20 can be removed through line 22 to the separation unit 23,
10 from which gaseous components can be returned to the reactor 20 through line 24 and the polymer product can be transferred through line 25 to an optional second separation unit 26. Gaseous or other components can be further separated and removed through line 27. The polymer product is transferred through line 28 to a pelletizing extruder or mixer 30, from which the final product is removed through line 31.

15 According to the invention the polymer through line 19, which polymer constitutes a part of the low molecular weight polymer produced in the first reactor 10, is transferred through line 19 to line 28. Through line 28 both polymer fractions are transferred to the mixing or pelletizing device 30 to form the product according to the invention.

20 In Figures 1 and 2 only the basic principle according to the invention is disclosed. Various modifications can be made concerning devices for separating portions from polymer flows, unreacted components etc. Such modifications can include cyclone separators or settling tank devices for dividing polymer flows into separate streams or
25 classifying low molecular weight polymer into fractions having certain particle size distribution. One preferable option according to the invention includes removing especially small particles or fine fractions from the first step polymerization product and transferring these fractions straight to the end product.

30 Figure 3 discloses a further modification of the process according to Figure 2. In this case a side feed extruder 40 is attached to the pelletizing mixer or extruder 30. The polymer portion separated from the first step polymerization product is transferred to the side feed extruder 40, where it is melted and led in molten condition to the extruder 30.

While the process according to the invention has been illustrated above as applied to two-step polymerization process, it is to be understood that both the first step polymerization and the second step polymerization can comprise two or more polymerization reactors in tandem. Such modifications belong also to the scope of the invention. It is also to be understood that each polymerization step can be carried out as a slurry polymerization, gas phase polymerization or even as a solution polymerization.

The invention is further illustrated by referring to the following examples, in which a combination of loop-gas phase-polymerization was used for producing bimodal high density polyethylene. Ethylene was first polymerized in a pilot-scale loop-reactor having a production capacity of about 50 kg/h and in a gas-phase reactor having a capacity of about 75 kg/h. The catalyst added to the loop reactor was a Ziegler-type catalyst containing magnesium, titanium and chlorine on a silica carrier prepared as described in Finnish patent n:o 89500. Hydrogen was used as a modifier and propane as diluent in the loop reactor.

In runs 1-3 the whole loop reactor product was introduced into the gas phase reactor. In runs 4-5 a part of the loop reactor product was separated according to the invention and combined with the gas phase reactor product and melted in an extruder (ZSK-30, Werner-Pfleiderer) for pelletizing the product. In runs 6-10 a part of the loop reactor product was separated according to the invention and melted in a side extruder, which was attached to the side of the main extruder.

The properties of the reactor and end products in runs 1-10 are presented in the following Table 1. It is evident from the table that a great amount of gels is produced, when the product split is high and the whole loop reactor product was introduced to the gas phase reactor (62:38-57:43 in runs 1-3). In runs 4-7 according to the invention, where also a high reactor splits in the end product was used, but a part of the loop reactor product was separated and combined with the gas-phase reactor product, where the reactor split was lower, much lower gel contents are achieved. The lowest gel contents were achieved when the product portion separated from the loop reactor product was melted before combining it with the product of the gas phase reactor.

Runs 11-17 were performed by using the same polymerization procedure as in runs 1-10. Brabender-extruder was used to combine the portion separated from the loop reactor product with the gas reactor product. The properties of the reactor and end products are presented in the Table 2.

TABLE I

Run	1	2	3	4	5	6	7	8	9	10
<u>Loop reactor product:</u>										
Density (g/dm ³)	970	971	972.3	971.8	972.3	971.8	972.3	973.2	972.2	971.7
MFR ₂ (g/10 min at 190°C)	20	90	165	116	165	116	165	244	149	116
M _w				28920			25000	21700	26280	
Product to gas-phase (%)	100	100	100	56.2	56.3	56.2	56.3	62.7	59.3	66.9
By-pass of gas-phase (%)	-	-	-	43.8	43.7	43.8	43.7	30.3	40.7	33.1
<u>Gas-phase product:</u>										
Density (g/dm ³)	949.6	948.8	952.5	944.5	944.0	944.5	944.0	948.8	950	951.0
M _w				464000			370000			
M _w /M _n				16		20				
MFR ₃ (g/10 min, 190°C)	0.9	0.5	0.6							
MFR ₃₁ (g/10 min, 190°C)	7.8	7.9	8.9	1.7	1.52	1.7	1.52	8	6	13
Reactor split low M _w /high M _w	62:38	57:43	57:43	45:55	46:54	45:55	46:54	46:54	45:55	45:55
<u>End product:</u>										
Density (g/dm ³)	949.6	948.8	952.5	953.5	953.7	952.5	953.4	953	955	955.0
Product split low M _w /high M _w	62:38	57:43	57:43	60:40	60:40	60:40	60:40	55:45	58:42	55:45
MFR ₃ (g/10 min, 190°C) (measured from pellets)	0.28	0.27	0.30	0.40	0.31	0.47	0.28	0.494	1.36	0.867
M _w		320		247	276	244	306			
M _w /M _n		17.2		17.0	21.8	16.7	27.2			
Gels/m ³	13500	8700	9100	3010	3100	1800	2100	1200	240	310
CTL (6.5 MPa)			133				143			

CTL = Const. tensile load at 6.5 MPa

TABLE 2

Run	11	12	13	14	15	16	17
<u>Loop reactor product:</u>							
Density (g/dm ³)	973.2	973.2	973.3	971.7	971.7	971.7	971.7
MFR ₂ (g/10 min at 190°C)	245	245	245	116	116	116	116
Product to gas-phase (%)	80.0	71.4	65.0	90.0	77.8	69.1	62.5
By-pass of gas-phase (%)	20.0	28.6	35.0	10.0	22.2	30.9	37.5
<u>Gas-phase product:</u>							
Density (g/dm ³)	949.1	949.1	949.1	944.5	944.5	944.5	944.5
MFR ₂₁ (g/10 min, 190°C)	5.2	5.2	5.2	2.16	2.16	2.16	2.16
Reactor split low M _w /high M _w	46:54	46:54	46:54	45:55	45:55	45:55	45:55
<u>End product:</u>							
Density (g/dm ³)			955		949	952	952
Product split low M _w /high M _w	55:45	58:42	60:40	50:50	55:45	58:42	60:40
MFR ₂₁ (g/10 min, 190°C) (measured from pellets)	15.7	21.6	27.6	3.33	5.4	8.28	11.1
Gels/m ²	42	170	580	13	145	130	490

SUBSTITUTE SHEET

Claims:

1. A process for producing bimodal olefin homopolymers or copolymers, said process comprising melting and mixing together under shear forces at least two polymer components of
 - (a) 5-50 percent by weight of a unimodal low molecular weight olefin polymer having a weight average molecular weight (M_w) within the range of 15,000 to 30,000 and a ratio between the weight average molecular weight (M_w) and the number average molecular weight (M_n) within the range of 2.5-9 and a melt index of 10-1000 g/10 min ($MFR_2, 190^\circ\text{C}$); and
 - (b) 95-50 percent by weight of a bimodal olefin polymer containing 30-55 per cent by weight of low molecular weight polyolefin fractions having properties as defined for component (a) above and 70-45 per cent by weight of polyolefin fractions having a molecular weight sufficiently high to achieve in the end product formed by components (a) and (b) a weight average molecular weight (M_w) within the range 150,000-400,000, M_w/M_n between 10-40 and a ratio between low molecular weight fractions and high molecular weight fractions (product split) of 40:60-70:30.
2. A process according to claim 1, comprising melting together 5-50 percent by weight of component (a) and 95-50 percent by weight of component (b), which contains 30-55 percent by weight of low molecular weight polyolefin component (c) and 70-45 per cent by weight of high molecular weight component (d), whereby components (a) and (c) originate from the same polymerization reaction.
3. A process for producing bimodal olefin homopolymers or copolymers, comprising melting and mixing together under shear forces at least two components of
 - (a) 5-50 percent by weight of a low molecular weight olefin polymer having a weight average molecular weight (M_w) within the range of 15,000-30,000 and a ratio between the weight average molecular weight (M_w) and the number average molecular weight (M_n) within the range of 2.5 to 9 and the melt index between 10-1000 g/10 min ($MFR_2, 190^\circ\text{C}$);

and

- (b) 95-55 percent by weight of a bimodal olefin polymer produced in at least one polymerization step sequence comprising a first polymerization step for polymerizing
5 olefin under polymerizing conditions to form a polymer component having low molecular weight and relatively narrow molecular weight distribution as defined for component (a) above, introducing at least part of said polymer into a second polymerization step for producing olefin polymer containing said low molecular weight polymer and high molecular weight polymer having a calculated M_w within the range of 250,000-700,000
10 and the ratio of M_w/M_n within the range of 4.5-9.5, whereby the product formed in the second polymerization step contains low molecular weight fractions within the range of 30-55 percent by weight and high molecular weight fractions within the range of 70-45 percent by weight.
- 15 4. A process according to claims 1-3, wherein component (a) is formed in at least one slurry polymerization step, preferably in a loop polymerization step.
5. A process according to any of the preceding claims, wherein said component (b) is formed in at least one gas-phase polymerization step.
- 20 6. A process according to claims 1-3, wherein said components (a) and (b) are formed in two slurry polymerization steps or in two gas-phase polymerization steps.
7. A process according to any of claims 1-6 for producing bimodal olefin homopolymers
25 or copolymers in at least one polymerization step sequence comprising polymerizing in a first polymerization step low molecular weight olefin polymer having a weight average molecular weight (M_w) within the range of 15,000 to 30,000 and a ratio between the weight average molecular weight (M_w) and the number average molecular weight (M_n) within the range of 2.5-9, introducing said polymer into a second polymerization step for
30 producing olefin polymer containing said low molecular weight polymer and high molecular weight olefin polymer having a calculated M_w within the range of 250,000-700,000 and a ratio of M_w/M_n within the range of 4.5 to 9.5, the product formed in the second polymerization step having a ratio between the low molecular weight material and the high

molecular material within the range of 30:70-55:45, wherein 5-50 per cent by weight of the polymer formed in said first polymerization step is separated and melt-mixed with the product of the second polymerization step thereby forming a polymer composition having a ratio of low molecular weight polymer fractions to high molecular weight polymer fractions (product split) within the range of 40:60-60:40.

8. A process according to claim 7, wherein the first step polymerization is carried out in a loop reactor and the second step polymerization is carried out in a gas phase reactor.

9. A process according to claim 6 or 7, wherein the product from the first polymerization step is classified to separate the fines, which are passed by the second polymerization step and combined by melt-mixing with the product coming from the second polymerization step.

10. A process according to any of the preceding claims, wherein said first component (a) and said component (b) are mixed together and melted, for example in a pelletizing device.




11. A process according to any of the claims 1-10, wherein said components (a) and (b) are melted before mixing together with each other.

12. A process according to claim 11, wherein said component (a) is melt-mixed in a side extruder attached to the pelletizing extruder for said second component (b).

13. Bimodal olefin homo and copolymers prepared by a process according to any of the preceding claims.

14. Olefins homo and copolymers according to claim 13, wherein said olefin is selected from the group of ethylene, propylene, butene, hexene and 4-methyl-1-pentene.

1/1



INTERNATIONAL SEARCH REPORT

International application No.

PCT/FI 94/00110

A. CLASSIFICATION OF SUBJECT MATTER

IPC 5: C08L 23/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 5: C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP, A2, 0517222 (HOECHST AKTIENGESSELLSCHAFT), 9 December 1992 (09.12.92), claim 1 --	1-14
A	EP, A1, 0533160 (PHILLIPS PETROLEUM COMPANY), 24 March 1993 (24.03.93), abstract, example B1 --	1-14
A	EP, A1, 0129312 (ASAHI KASEI KOGYO KABUSHIKI KAISHA), 27 December 1984 (27.12.84), page 11 - page 12, abstract -- -----	1-14

☐ Further documents are listed in the continuation of Box C.
 ☒ See patent family annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

27 June 1994

Date of mailing of the international search report

13 -07- 1994

Name and mailing address of the ISA/
Swedish Patent Office
Box 5055, S-102 42 STOCKHOLM
Facsimile No. +46 8 666 02 86

Authorized officer

Barbro Nilsson
Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT
Information on patent family members

28/05/94

International application No.

PCT/FI 94/00110

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A2- 0517222	09/12/92	NONE	
EP-A1- 0533160	24/03/93	JP-A- 5194796	03/08/93
EP-A1- 0129312	27/12/84	CA-A- 1218181	17/02/87
		DE-A- 3470168	05/05/88
		JP-B- 1012777	02/03/89
		JP-C- 1612249	30/07/91
		JP-A- 59196345	07/11/84
		US-A- 4536550	20/08/85
		JP-B- 1012778	02/03/89
		JP-C- 1612250	30/07/91
		JP-A- 59196346	07/11/84
		JP-A- 60036546	25/02/85
		JP-B- 1012781	02/03/89
		JP-C- 1612255	30/07/91
		JP-A- 60036547	25/02/85